



Sun Prosper Chemicals Limited

Tel: (852) 2656 9128

Fax: (852) 2656 9108

J800R is a well designed polypropylene that features high flowability and excellent long term heat stability for injection molding applications. UL 746B(120°C)

Applications : Home appliances(Steamer, Electric sauna parts, Electric jar, Coffee maker etc.)

PROPERTIES	TEST METHOD	UNIT	J800R
Melt index	ASTM D1238	g/10 min	10
Tensile strength(yield)	ASTM D638	kg/cm ²	280
Elongation(Break)	ASTM D638	%	500
Flexural Modulus	ASTM D790	kg/cm ²	12,000
Izod Impact strength	23°C		10
	-10°C	ASTM D256	kg-cm/cm
Rockwell hardness	ASTM D785	R-Scale	80
Vicat Softening Point	ASTM D1525	°C	150
Heat-Deflection temperature(4.6kg/cm ²)	ASTM D648	°C	105

* The data are relative and represent empirical values obtained in various tests.